

PRODUCT Nº : 1.528

## IMPERMEABILIZANTE E-88

### WATERPROOFING COATING FOR TERRACES

#### DESCRIPTION:

**IMPERMEABILIZANTE E-88** is a coating formulated based on innerly plasticised resins in aqueous dispersion, which offers the best properties of waterproofness, weather resistance and excellent elasticity.

The coating resists great temperature variations, not losing its waterproofing or resistance properties.

#### CHARACTERISTICS:

Density	:	1,27 ± 0,05 gr./cm. <sup>3</sup>
Appearance	:	Tixotropic dispersion
Drying time at 20°C and 55% H.R.	:	Touch 2 hours - Total 8 hours Repainted, min. 8 hours.
Recommended amount	:	2 kg./m <sup>2</sup> in several coats
Application	:	Brush or roller
Thinner	:	Water
Adherence	:	Perfect on properly conditioned supports

#### FIELDS OF APPLICATION:

As waterproofing for terraces, roofs, joints between roof and vertical walls, flat roofs, waterways, façades, fibercement roofs, etc.

It should not be applied on surfaces which are to be in permanent contact with water or for waterproofings which are to be paved on top.

#### SURFACES CONDITIONING:

Surfaces must be dry and free from grease, oil, dust or any other pollutant.

Surfaces with no roughness or porosity need to be mechanically or chemically roughened with our **DESCA-2F**, rinsing with plenty of water in order to remove every product remains.

#### METHOD OF USE:

Before using the product it's recommended to stir the containers. Once the surface is conditioned, apply the first coat of **IMPERMEABILIZANTE E-88** diluted with 10% water and spread covering the whole area.

Apply the second coat after 8 hours, non-diluted and trying to leave higher thickness. The rest of coats must wait the above mentioned repainting periods.

In cracks it's recommended to apply our **TELA DE ARMAR** made of glass fibre, alongside, with a width of about 15-20 cm. After the first coat, when it's still wet, place the fabric pressing with the roller in order to soak it in product.

In joints between floor and wall, the product should go up for about 25 cm.

If it's desired to place **TELA DE ARMAR** on the whole surface to be waterproofed, it will be placed after the first coat, when it's still wet and pressing with the roller in order to soak the fabric. In joints between wall and floor, the fabric should go up the wall about 25 cm, just like the product.

In order to assure a perfect waterproofing, it's recommended to apply 2 kg per square meter in several coats, with different colours in order to check there are no uncovered areas.

### SPECIAL RECOMMENDATIONS:

It's not recommended its application in the following conditions:

- If rain is expected before total drying of the product.
- If there were risk of frost in 12 hours after applying the product.
- If temperature is below 12 °C.
- If relative humidity is above 80%.

When weather conditions are critical, not reaching the above mentioned ones:

- Use the hours in the day when the temperature is the highest.
- Apply thinner coats.
- Increase repainting periods up to 24 or 48 hours in order to assure good drying of the applied coats.

### STORAGE:

The product must be stored in tightly closed containers, and protected from frost. The storage life in these conditions is 1 year.

### COLOURS:

**IMPERMEABILIZANTE E-88** is supplied in white, grey, cream, red, green and black.

### PACKAGING:

25 kg plastic containers.

### ADVANTAGES

- Easy application.
- Long-lasting roof waterproofing.
- Permanent elasticity with time.

ED.2001/3